

Single-order-parameter description of glass-forming liquids

A one-frequency test

Ellegaard, Niels Langager; Christensen, Tage Emil; Christiansen, Peder Voetmann; Olsen, Niels Boye; Pedersen, Ulf Rørbæk; Schrøder, Thomas; Dyre, Jeppe

Published in:
Journal of Chemical Physics

DOI:
[10.1063/1.2434963](https://doi.org/10.1063/1.2434963)

Publication date:
2007

Document Version
Publisher's PDF, also known as Version of record

Citation for published version (APA):
Ellegaard, N. L., Christensen, T. E., Christiansen, P. V., Olsen, N. B., Pedersen, U. R., Schrøder, T., & Dyre, J. (2007). Single-order-parameter description of glass-forming liquids: A one-frequency test. *Journal of Chemical Physics*, 126(7), 074502-1 - 074502-8. <https://doi.org/10.1063/1.2434963>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain.
- You may freely distribute the URL identifying the publication in the public portal.

Take down policy

If you believe that this document breaches copyright please contact rucforsk@kb.dk providing details, and we will remove access to the work immediately and investigate your claim.

Single-order-parameter description of glass-forming liquids: A one-frequency test

Niels L. Ellegaard, Tage Christensen, Peder Voetmann Christiansen, Niels Boye Olsen, Ulf R. Pedersen, Thomas B. Schröder, and Jeppe C. Dyre
DNRF Centre "Glass and Time," IMFUFA (27), Department of Sciences, Roskilde University, Postbox 260, DK-4000 Roskilde, Denmark

(Received 1 November 2006; accepted 28 December 2006; published online 15 February 2007)

Thermoviscoelastic linear-response functions are calculated from the master equation describing viscous liquid inherent dynamics. From the imaginary parts of the frequency-dependent isobaric specific heat, isothermal compressibility, and isobaric thermal expansion coefficient, we define a "linear dynamic Prigogine-Defay ratio" $\Lambda_{Tp}(\omega)$ with the property that if $\Lambda_{Tp}(\omega)=1$ at one frequency, then $\Lambda_{Tp}(\omega)$ is unity at all frequencies. This happens if and only if there is a single-order-parameter description of the thermoviscoelastic linear responses via an order parameter (which may be nonexponential in time). Generalizations to other cases of thermodynamic control parameters than temperature and pressure are also presented. © 2007 American Institute of Physics.
 [DOI: 10.1063/1.2434963]

I. INTRODUCTION

A famous result of classical glass science is that if a glass-forming liquid is described by a single-order parameter, the Prigogine-Defay ratio is unity. Recall that if Δc_p is the difference between liquid and glass isobaric specific heat per unit volume at the glass transition temperature T_g , $\Delta \kappa_T$ the similar liquid-glass difference of isothermal compressibilities, and $\Delta \alpha_p$ the difference of isobaric thermal expansion coefficients, the Prigogine-Defay ratio Π is defined¹⁻³ by

$$\Pi = \frac{\Delta c_p \Delta \kappa_T}{T_g (\Delta \alpha_p)^2}. \quad (1)$$

Both experimentally and theoretically the following inequality was established early on: $\Pi \geq 1$.¹⁻⁹ The vast majority of reported Π 's are significantly larger than unity,¹⁰ and for decades the consensus has been that—possibly with a few exceptions^{11,12}—a single-order parameter is not sufficient for describing glass-forming liquids.

The above picture came about as follows. The glass transition is a freezing of configurational degrees of freedom. If kinetic aspects are ignored, the glass transition has the appearance of a second-order phase transition in the Ehrenfest sense with continuity of volume and entropy, but discontinuity of their thermodynamic derivatives. If the "order parameters" (numbers characterizing the structure) are denoted by z_1, \dots, z_k , these are frozen in the glass phase. In the equilibrium liquid phase the order parameters depend on pressure and temperature, a dependence that is determined by minimizing Gibbs free energy $G(T, p, z_1, \dots, z_k)$: $\partial G / \partial z_i = 0$.³ In the classical papers by Davies and Jones from the 1950s^{1,2} it was shown that within this framework one always has $\Pi \geq 1$ and that $\Pi=1$ if there is just a single-order parameter. The simplest dynamics for the approach to equilibrium for the order parameters $\dot{z}_i = -\Lambda_i \partial G / \partial z_i$ imply exponential decays for each order parameter for small perturbations from

equilibrium. Under this assumption, in the case of just one order parameter any quantity relaxes exponentially to equilibrium after a small disturbance. Exponential relaxations of the macroscopic variables are seldom observed, although there is evidence that relaxation is often intrinsically exponential so that the nonexponential behavior comes from a distribution of exponential relaxations.¹³⁻¹⁵ This reflects dynamic heterogeneity. Historically the fact that macroscopic relaxations are nonexponential was often taken as confirming the conventional wisdom that one order parameter is rarely not enough.—Besides the reported Prigogine-Defay ratios being almost always significantly larger than unity, a further classical argument for the necessity of more than one order parameter is the following:¹⁶ If structure were characterized by a single-order parameter, glasses with the same index of diffraction would also have all other physical properties identical, which is not the case. This does not rule out the possibility that a single-order parameter is sufficient to describe the linear thermoviscoelastic response of the viscous liquid phase, however, and it is this possibility we shall inquire into in the present paper.

Because kinetic aspects cannot be ignored, the glass transition is not a phase transition. Thus, there is no exact T_g and strictly speaking the Π of Eq. (1) is not well defined. This is because the properties of a glass depend to some extent on the cooling history; moreover, extrapolations from the glass phase are somewhat ambiguous because glass properties change slightly with time. Thus the changes in specific heat, etc., found by extrapolating glass and liquid specific heats from below and above, respectively, to T_g (Ref. 17) are not rigorously well defined. This weakens the generally accepted conclusion that in the vast majority of cases there must be more than one order parameter.

The problem of making the Prigogine-Defay ratio rigorously well defined is solved by referring exclusively to linear-response experiments on the equilibrium viscous liq-

uid phase.^{16,18,19} In viscous liquids, thermodynamic coefficients are generally frequency dependent, $c_p = c_p(\omega)$, etc. The high-frequency limits reflect glassy behavior where relaxations do not have enough time to take place, corresponding to “frozen” structure. Thus for the equilibrium viscous liquid phase at any given temperature T one redefines Eq. (1) to be the “linear Prigogine-Defay ratio” given^{16,18,19} by

$$\Pi = \frac{[c_p(\omega \rightarrow 0) - c_p(\omega \rightarrow \infty)][\kappa_T(\omega \rightarrow 0) - \kappa_T(\omega \rightarrow \infty)]}{T[\alpha_p(\omega \rightarrow 0) - \alpha_p(\omega \rightarrow \infty)]^2}. \quad (2)$$

Descriptions of viscous liquids and the glass transition by means of one or more order parameter were actively discussed in the 1970s.^{16,18–22} Since the Π of Eq. (1) is not well defined and since there are no measurements of the linear Prigogine-Defay ratio of Eq. (2), the question of one or more order parameters remains open.^{23,24} In our view, there are a number of reasons to take seriously the possibility that some glass-forming liquids may be described by a single order parameter: (1) In early computer simulations Clarke reported Prigogine-Defay ratios close to one for a 216 particle Lennard-Jones model of Argon.²⁵ This is not a highly viscous liquid, but recent extensive simulations by Sciortino and coworkers of viscous liquids confirmed this scenario by showing that structural relaxations for small temperature changes are basically controlled by a single parameter (e.g., the volume).^{26–29} (2) Experiments monitoring loss peak frequency and loss maximum of the Johari-Goldstein dielectric beta relaxation process upon temperature jumps revealed a striking correlation between these two quantities, a correlation which is difficult to explain unless structure is parametrized by a single-order parameter.³⁰ In these experiments the relaxation of beta process properties is controlled by the alpha relaxation time. This is to be expected because the alpha time is the structural relaxation time, but it is highly nontrivial that alpha and beta relaxations correlate in equilibrium viscous liquids, as shown recently by Böhmer and coworkers;³¹ this may be taken as a further indication that a single order parameter controls the behavior. (3) Experiments studying dielectric relaxation under varying temperature and pressure conditions showed that the shape of the alpha loss peak as quantified by the stretching exponent β depends only on the loss peak frequency.³² This could be a consequence of there being just one order parameter, determining both alpha relaxation time and stretching. (4) Finally, we would like to mention theoretical works suggesting that the Prigogine-Defay ratio may be unity in some cases.^{23,33,34} More speculatively, in our opinion it would not be too surprising if there is just one order parameter for liquids where time-temperature superposition applies accurately, because in these liquids linear relaxations appear to be particularly simple with a generic $\omega^{-1/2}$ high-frequency decay of, e.g., the dielectric and mechanical alpha loss peaks.^{35,36}

The wide-frequency measurements required to determine Π of Eq. (2) will probably be difficult to perform in the foreseeable future. There are, in fact, no measurements of all three required frequency-dependent thermoviscoelastic linear-response functions. Work at our laboratory indicates

that such measurements are possible,³⁷ but only over a limited frequency range. This motivates a search for an alternative to the linear Prigogine-Defay ratio. In this article, we introduce a “linear dynamic Prigogine-Defay ratio” (where the double prime indicates the imaginary part of the corresponding frequency-dependent linear-response function):

$$\Lambda_{Tp}(\omega) = \frac{c_p''(\omega)\kappa_T''(\omega)}{T_0(\alpha_p''(\omega))^2}. \quad (3)$$

Based on the description of viscous liquid dynamics in terms of Markovian inherent dynamics, in Secs. II and III we prove that $\Lambda_{Tp}(\omega) = 1$ if and only if the linear Prigogine-Defay ratio [Eq. (2)] is unity. This happens if and only if there is a single, generally nonexponential order parameter. Moreover, it is proved that if $\Lambda_{Tp}(\omega) = 1$ at one frequency, this is true at all frequencies. In Sec. IV we investigate the matter in a thermodynamic approach and prove that in this framework the existence of a single-order parameter implies that $\Lambda_{Tp}(\omega) = 1$ at all frequencies. In the Appendix it is shown that $\Lambda_{Tp}(\omega)$ is just one out of a family of four linear dynamic Prigogine-Defay ratios larger than or equal to one, which equal unity if and only if there is a single order parameter.

II. RESPONSE MATRIX FOR MARKOVIAN INHERENT DYNAMICS

Adopting the energy landscape approach to viscous liquid dynamics³⁸ we model the liquid (henceforth: “system”) by the inherent dynamics consisting of jumps between the potential energy minima.^{29,39–41} This description is believed to be realistic in the highly viscous phase where there is a clear separation between the vibrational time scales (in the picosecond range) and the (alpha) relaxation time scale—the time scale of interest here. If the system has N potential energy minima, an ensemble of similar systems is described by a vector of probabilities $\mathbf{P} = (P_1, P_2, \dots, P_N)$, where P_n denotes the fraction of systems vibrating around energy minimum n . If $G_n(T, p)$ denotes the vibrational Gibbs free energy of minimum n , the \mathbf{P} -dependent Gibbs free energy is defined³⁹ by

$$G(T, p, \mathbf{P}) = \sum_n P_n (G_n(T, p) + k_B T \ln P_n). \quad (4)$$

Via the standard thermodynamic identities the \mathbf{P} -dependent entropy S and volume V are given by

$$S(T, p, \mathbf{P}) = - \sum_n P_n \left(\frac{\partial G_n}{\partial T} + k_B \ln P_n \right), \quad (5)$$

$$V(T, p, \mathbf{P}) = \sum_n P_n \frac{\partial G_n}{\partial p}.$$

It is convenient to introduce the notation $\mathbf{X} = (T, -p)$ for the controlled (“input”) variables and $\mathbf{Q} = (S, V)$ for the induced responses (“output”). Thus

$$Q_\alpha = -\frac{\partial G}{\partial X_\alpha}, \quad \alpha = 1, 2. \quad (6)$$

The equilibrium probability distribution is found by minimizing $G(T, p, \mathbf{P})$ under the constraint $\sum_n P_n = 1$; this leads⁴² to the well-known canonical probabilities (where $G(T, p)$ is the Gibbs free energy of Eq. (4) evaluated at the equilibrium probabilities)

$$P_n^{\text{eq}}(T, p) = \exp\left(-\frac{G_n(T, p) - G(T, p)}{k_B T}\right). \quad (7)$$

Inherent dynamics consist of transitions between minima.⁴¹ The inherent dynamics are modeled as a Markov process; thus the probabilities obey a standard master equation⁴³

$$\dot{P}_n = \sum_m W_{nm} P_m. \quad (8)$$

The rate matrix W and the equilibrium probability distribution P_n^{eq} both depend on T and p , and for all n one has

$$\sum_m W_{nm}(T, p) P_m^{\text{eq}}(T, p) = 0. \quad (9)$$

In the following the variables T and p are assumed to vary slightly from their average values T_0 and p_0 as arbitrary externally-controlled functions of time, resulting in small changes of S and V . Examining perturbations around the reference state $\mathbf{X}_0 = (T_0, -p_0)$ it is convenient to introduce the notation $W_{nm}^0 \equiv W_{nm}(T_0, p_0)$ and $P_n^0 \equiv P_n^{\text{eq}}(T_0, p_0)$. If δ denotes perturbations from the reference state, $P_n(t) = P_n^0 + \delta P_n(t)$, etc., Eq. (8) implies to first order

$$\delta \dot{P}_n = \sum_m (W_{nm}^0 \delta P_m + \delta W_{nm} P_m^0). \quad (10)$$

Since $\delta(\sum_m W_{nm} P_m^{\text{eq}}) = 0$ [Eq. (9)], one has $\sum_m \delta W_{nm} P_m^0 = -\sum_m W_{nm}^0 \delta P_m^{\text{eq}}$. When this is substituted into Eq. (10) we get

$$\delta \dot{P}_n = \sum_m W_{nm}^0 (\delta P_m - \delta P_m^{\text{eq}}). \quad (11)$$

Next, we expand δP_m^{eq} in terms of δX_α . Equations (5) and (7) imply⁴⁴ (where $\beta = 1, 2$ and $\delta_{\beta 1}$ is the Kronecker delta symbol)

$$\frac{\partial \ln P_m^{\text{eq}}}{\partial X_\beta} = \frac{1}{k_B T} \left(\frac{\partial Q_\beta}{\partial P_m} - Q_\beta + \delta_{\beta 1} k_B \right). \quad (12)$$

Thus to lowest order

$$\delta P_m^{\text{eq}} = \frac{P_m^0}{k_B T_0} \left[\left(\frac{\partial Q_1}{\partial P_m} - Q_1 + k_B \right) \delta X_1 + \left(\frac{\partial Q_2}{\partial P_m} - Q_2 \right) \delta X_2 \right]. \quad (13)$$

Inserting this into Eq. (11) and utilizing Eq. (9) we arrive at the following ‘‘equation of motion’’ for the probabilities when temperature and pressure vary slightly as arbitrary functions of time [$\delta X_\beta \equiv \delta X_\beta(t)$]:

$$\delta \dot{P}_n = \sum_m W_{nm}^0 \left(\delta P_m - \frac{1}{k_B T_0} \sum_\beta P_m^0 \frac{\partial Q_\beta}{\partial P_m} \delta X_\beta \right). \quad (14)$$

Consider now a harmonic linear perturbation of the system. In relaxing systems like glass-forming liquids the ordinary thermodynamic response functions are frequency dependent and complex. Writing $T(t) = T_0 + \text{Re}(\delta T e^{i\omega t})$ and $p(t) = p_0 + \text{Re}(\delta p e^{i\omega t})$, the oscillations of S and V are similarly described by $S(t) = S_0 + \text{Re}(\delta S e^{i\omega t})$ and $V(t) = V_0 + \text{Re}(\delta V e^{i\omega t})$. If δP_n and δX_β denote the (complex) frequency-dependent amplitudes, in steady state Eq. (14) implies that

$$\sum_n (W_{ln}^0 - i\omega \delta_{ln}) \delta P_n = \frac{1}{k_B T_0} \sum_{m,\beta} W_{lm}^0 P_m^0 \frac{\partial Q_\beta}{\partial P_m} \delta X_\beta. \quad (15)$$

For $\omega > 0$ we solve Eq. (15) by defining (where I is the identity matrix)

$$A_{nm}(\omega) = \frac{1}{k_B T_0} \sum_l (W^0 - i\omega I)_{nl}^{-1} W_{lm}^0 P_m^0, \quad (16)$$

leading to the following equation for the frequency-dependent complex probability amplitudes:

$$\delta P_n = \sum_{m,\beta} A_{nm}(\omega) \frac{\partial Q_\beta}{\partial P_m} \delta X_\beta. \quad (17)$$

In order to calculate the thermoviscoelastic linear-response functions we first define $J_{\alpha\beta}^\infty = (\partial Q_\alpha / \partial X_\beta)$. This symmetric 2×2 matrix gives the instantaneous (glassy) linear response because it determines the variations of S and V when the probabilities P_n are frozen.³⁹ Next, we expand the frequency-dependent complex amplitudes δQ_α to get

$$\delta Q_\alpha = \sum_n \frac{\partial Q_\alpha}{\partial P_n}(T_0, p_0) \delta P_n + \sum_\beta J_{\alpha\beta}^\infty \delta X_\beta. \quad (18)$$

Here and henceforth, for any function f the notation $f(T_0, p_0)$ for a variable that also depends on the probabilities \mathbf{P} signifies that f is evaluated at the equilibrium probabilities [Eq. (7)]. When Eq. (17) is inserted into Eq. (18), we get

$$\delta Q_\alpha = \sum_\beta J_{\alpha\beta}(\omega) \delta X_\beta, \quad (19)$$

where

$$J_{\alpha\beta}(\omega) = J_{\alpha\beta}^\infty + \sum_{m,n} \frac{\partial Q_\alpha}{\partial P_n}(T_0, p_0) A_{nm}(\omega) \frac{\partial Q_\beta}{\partial P_m}(T_0, p_0). \quad (20)$$

Since $A_{nm}(\omega \rightarrow \infty) = 0$ it follows that $J_{\alpha\beta}(\omega \rightarrow \infty) = J_{\alpha\beta}^\infty$, justifying the notation.

We proceed to show that the 2×2 -matrix $J_{\alpha\beta}(\omega)$ is symmetric. Introducing the matrix Y_{nm} defined by

$$Y_{nm} = (P_n^0)^{-1/2} W_{nm}^0 (P_m^0)^{1/2}, \quad (21)$$

the detailed-balance requirement implies that Y is symmetric.^{43,45} For later use we note that Y is negative semidefinite.⁴³ For all vectors x one has $\langle x | Y | x \rangle \leq 0$. Moreover, equality applies if and only if $x \propto (P^0)^{1/2}$; the latter property of Y expresses ‘‘ergodicity,’’ i.e., the assumption about the master equation that all states are connected by some sequence of transitions. We define a diagonal matrix R by

$$R_{nm} = (P_n^0)^{1/2} \delta_{nm} \quad (22)$$

and note that $W^0 = RYR^{-1}$. This implies that

$$\begin{aligned} A(\omega) &= \frac{1}{k_B T_0} (W^0 - i\omega I)^{-1} W^0 R^2 \\ &= \frac{1}{k_B T_0} (R(Y - i\omega I)R^{-1})^{-1} RYR \\ &= \frac{1}{k_B T_0} R(Y - i\omega I)^{-1} YR. \end{aligned} \quad (23)$$

Since Y and R are both symmetric, it follows that $A(\omega)$ is symmetric. Thus by Eq. (20) the 2×2 matrix $J_{\alpha\beta}(\omega)$ is symmetric.

The $J_{\alpha\beta}(\omega)$ matrix determines the frequency-dependent thermoviscoelastic linear response defined as follows: If $c_p(\omega)$ denotes the isobaric heat capacity per unit volume, $\alpha_p(\omega)$ the isobaric thermal-expansion coefficient, and $\kappa_T(\omega)$ the isothermal bulk compressibility, the complex frequency-

dependent coefficients δT , δp , δS , and δV are related by the following matrix (the symmetry of which reflects the symmetry of $J_{\alpha\beta}(\omega)$):

$$\begin{pmatrix} \delta S \\ \delta V \end{pmatrix} = V_0 \begin{pmatrix} c_p(\omega)/T_0 & \alpha_p(\omega) \\ \alpha_p(\omega) & \kappa_T(\omega) \end{pmatrix} \begin{pmatrix} \delta T \\ -\delta p \end{pmatrix}. \quad (24)$$

Whenever there is time-reversal invariance, the (dc, i.e., zero-frequency) symmetry implied by a Maxwell relation translates into (ac) Onsager reciprocity, a well-known result.^{43,45}

III. LINEAR DYNAMIC PRIGOGINE-DEFAY RATIO

We proceed to calculate the linear Prigogine-Defay ratio of Eq. (2) from the expression for the frequency-dependent linear response functions. Since $A_{nm}(\infty) = 0$, we find by inserting Eq. (20) into Eq. (2) [with $T = T_0$ and where $\partial S / \partial P_n \equiv \partial S / \partial P_n(T_0, p_0)$ and $\partial V / \partial P_n \equiv \partial V / \partial P_n(T_0, p_0)$ but “ (T_0, p_0) ” is left out for brevity]

$$\Pi = \frac{\left(\sum_{m,n} \frac{\partial S}{\partial P_n} A_{nm}(0) \frac{\partial S}{\partial P_m} \right) \left(\sum_{m,n} \frac{\partial V}{\partial P_n} A_{nm}(0) \frac{\partial V}{\partial P_m} \right)}{\left(\sum_{m,n} \frac{\partial S}{\partial P_n} A_{nm}(0) \frac{\partial V}{\partial P_m} \right)^2}. \quad (25)$$

Next we reason in a way analogous to that of Davies and Jones² based on the Cauchy-Schwartz inequality. This inequality is the well-known mathematical theorem that if a real symmetric matrix \mathbf{B} is positive or negative semidefinite, the following applies: For any vectors x and y one has $\langle x | \mathbf{B} | y \rangle^2 \leq \langle x | \mathbf{B} | x \rangle \langle y | \mathbf{B} | y \rangle$, and for nonzero x and y equality applies if and only if a number γ exists such that $x - \gamma y \in N(\mathbf{B})$ where $N(\mathbf{B})$ is the kernel (null space) of \mathbf{B} . The matrix $A(0)$ is positive semidefinite and the kernel of $A(0)$ is the one-dimensional linear subspace spanned by the vector $(1, \dots, 1)$.⁴⁶ This implies that $\Pi \geq 1$ and that $\Pi = 1$ if and only if there are constants γ and c such that the following equations apply for all n (compare Refs. 2, 5, and 47):

$$\frac{\partial V}{\partial P_n}(T_0, p_0) = \gamma \frac{\partial S}{\partial P_n}(T_0, p_0) + c. \quad (26)$$

For reasons given in the next section this situation is referred to as the single-order-parameter case.

As mentioned in the Introduction, the linear Prigogine-Defay ratio of Eq. (2) is difficult to measure. Instead we propose to consider the “linear dynamic Prigogine-Defay ratio” defined in Eq. (3). When Eq. (20) is inserted into this we find

$$\Lambda_{Tp}(\omega) = \frac{\left(\sum_{m,n} \frac{\partial S}{\partial P_n} A''_{nm}(\omega) \frac{\partial S}{\partial P_m} \right) \left(\sum_{m,n} \frac{\partial V}{\partial P_n} A''_{nm}(\omega) \frac{\partial V}{\partial P_m} \right)}{\left(\sum_{m,n} \frac{\partial S}{\partial P_n} A''_{nm}(\omega) \frac{\partial V}{\partial P_m} \right)^2}. \quad (27)$$

Because the matrix $A''(\omega)$ is negative semidefinite for all $\omega > 0$,⁴⁶ the Cauchy-Schwartz inequality implies that $\Lambda_{Tp}(\omega) \geq 1$. Again, equality applies if and only if a number γ exists such that the vector with n th component $\partial V / \partial P_n - \gamma \partial S / \partial P_n$ is in the kernel of the matrix $A''(\omega)$, which is the one-dimensional space spanned by the vector $(1, \dots, 1)$.⁴⁶ Thus for all $\omega > 0$ the equation $\Lambda_{Tp}(\omega) = 1$ is mathematically equivalent to Eq. (26), and $\Lambda_{Tp}(\omega) = 1$ is equivalent to $\Pi = 1$.

In particular, if $\Lambda_{Tp}(\omega)$ is unity at one frequency, $\Lambda_{Tp}(\omega)$ is unity for all frequencies—and this happens precisely when $\Pi = 1$.

IV. WHY $\Pi = 1$ CORRESPONDS TO A SINGLE ORDER PARAMETER

We define the order parameter ε by

$$\delta\varepsilon(t) = \sum_n \frac{\partial S}{\partial P_n}(T_0, p_0) \delta P_n(t). \quad (28)$$

Combining Eq. (28) with Eqs. (18) and (26) we find that in any linear experiment (thus calculating to lowest order) S and V are functions of T , p , and $\delta\varepsilon$ (where $J_{12}^\infty = J_{21}^\infty$)

$$\delta S(t) = \delta\varepsilon(t) + J_{11}^\infty \delta T(t) - J_{12}^\infty \delta p(t), \quad (29)$$

$$\delta V(t) = \gamma \delta\varepsilon(t) + J_{21}^\infty \delta T(t) - J_{22}^\infty \delta p(t).$$

The situation described by these equations is more general than the single-order parameter model of Prigogine and Meixner,^{3,48} because Eq. (29) allows for an order parameter with nonexponential dynamics. The common physics, however, are that besides T and p one single number determines both entropy and volume fluctuations. In the present approach ε might well have a memory of the thermal prehistory.

By the definition we shall adopt here, the single-order-parameter situation applies whenever Eq. (29) is obeyed for some variable $\delta\varepsilon$. In the last section we proved that if $\Lambda_{Tp}(\omega) = 1$ applies at one frequency, then Eq. (29) follows. We proceed to show that conversely, if Eq. (29) applies for some order parameter ε , then $\Lambda_{Tp}(\omega) = 1$ for all ω . To prove this, consider a situation with periodically varying temperature and pressure fields. In steady state δS , δV , and $\delta\varepsilon$ vary periodically with complex amplitudes $\delta S(\omega)$, $\delta V(\omega)$, and $\delta\varepsilon(\omega)$. According to Eq. (29) these amplitudes are given by (for any ω)

$$\delta S(\omega) = \delta\varepsilon(\omega) + J_{11}^\infty \delta T(\omega) - J_{12}^\infty \delta p(\omega), \quad (30)$$

$$\delta V(\omega) = \gamma \delta\varepsilon(\omega) + J_{21}^\infty \delta T(\omega) - J_{22}^\infty \delta p(\omega).$$

In the case where only temperature varies, comparing to Eq. (24) shows that the following two equations apply:

$$\frac{V_0}{T_0} c_p(\omega) = \left(\frac{\delta S(\omega)}{\delta T(\omega)} \right)_p = \left(\frac{\delta\varepsilon(\omega)}{\delta T(\omega)} \right)_p + J_{11}^\infty, \quad (31)$$

$$V_0 \alpha_p(\omega) = \left(\frac{\delta V(\omega)}{\delta T(\omega)} \right)_p = \gamma \left(\frac{\delta\varepsilon(\omega)}{\delta T(\omega)} \right)_p + J_{21}^\infty.$$

Since the J^∞ 's are real numbers, we have

$$\gamma \frac{c_p''(\omega)}{T_0} = \alpha_p''(\omega). \quad (32)$$

Similarly, if only pressure varies Eqs. (30) and (24) imply

$$V_0 \alpha_p(\omega) = - \left(\frac{\delta S(\omega)}{\delta p(\omega)} \right)_T = - \left(\frac{\delta\varepsilon(\omega)}{\delta p(\omega)} \right)_T + J_{12}^\infty, \quad (33)$$

$$V_0 \kappa_T(\omega) = - \left(\frac{\delta V(\omega)}{\delta p(\omega)} \right)_T = - \gamma \left(\frac{\delta\varepsilon(\omega)}{\delta p(\omega)} \right)_T + J_{22}^\infty;$$

thus

$$\gamma \alpha_p''(\omega) = \kappa_T''(\omega). \quad (34)$$

Eliminating γ by combining Eqs. (32) and (34) yields $\Lambda_{Tp}(\omega) = 1$ for any ω . Note that in the case of one order

parameter the imaginary (“loss”) parts of all three response functions are proportional.

The above line of reasoning can be repeated for different choices of input and output variables. Altogether there are four different natural (linear) dynamic Prigogine-Defay ratios as demonstrated in the Appendix; here it is also shown that the requirement of positive dissipation implies that no dynamic Prigogine-Defay ratio can be smaller than unity.

V. CONCLUDING REMARKS

The original Prigogine-Defay ratio of Eq. (1) is not rigorously well defined. The “linear” Prigogine-Defay ratio of Eq. (2) is well defined, but requires measurements of thermoviscoelastic response functions over many decades of frequency. There are still no methods for measuring a complete set of these response functions. Hopefully such measurements are possible in the near future, but realistically they will initially only cover a few decades.³⁷ This motivates the one-frequency criterion proposed and developed mathematically in this article: If the linear dynamic Prigogine-Defay ratio is unity at one frequency, this quantity is unity at all frequencies and a single-order parameter description applies. Conversely, if a single-order parameter description applies, the dynamic Prigogine-Defay ratio is unity at all frequencies. If this happens, the imaginary parts of the three linear response functions of Eq. (24) are proportional. As shown in the Appendix, these results all generalize to the three other natural choices of input and output variables. These are strict mathematical statements; in practice one cannot determine whether or not the dynamic Prigogine-Defay ratio is precisely one. What one can do is test how close to unity is this quantity. We expect that a single-parameter description is a good approximation whenever the dynamic Prigogine-Defay ratio is close to unity. Note that if there are several relaxation processes with well-separated time scales, it is possible that some of these are well described by a single-order parameter, though not perfectly, whereas others are not. In this case the frequency-dependent one-parameter test developed here in principle would be useful although, as mentioned already, it will probably not be possible in the foreseeable future to determine all three required response functions over wide frequency ranges.

In the present paper we referred to the $\Lambda_{Tp} = 1$ situation as that of a single, generally nonexponential order parameter. As emphasized by Goldstein,⁵ however, due to a mathematical equivalence it is really a matter of taste whether one prefers instead to refer to a situation of several order parameters obeying a mathematical constraint [in our case Eq. (26)]. It is not possible *a priori* to estimate how restrictive or unlikely it is that Eq. (26) applies; only experiment can settle this question. It should be noted, though, that there is a simple physical interpretation of the single-order parameter case: In the approximation where each inherent state is regarded as a potential energy minimum with a harmonic potential, via Eqs. (5) and (7), Eq. (26) is equivalent to $V_n = \alpha_1 E_n + \alpha_2$ where V_n is the inherent state volume and E_n the inherent state energy (potential energy minimum). Thus there is a single-order parameter if and only if inherent state vol-

ume correlates perfectly and linearly with inherent state energy (in practice: for the dominant fluctuations at a given temperature). It is expected that this condition is obeyed to a good approximation if and only if the dynamic Prigogine-Defay ratio is close to unity.

ACKNOWLEDGMENTS

The authors wish to thank Nick Bailey for helpful comments. This work was supported the Danish National Research Foundation's (DNRF) center for viscous liquid dynamics "Glass and Time."

APPENDIX: GENERALIZATIONS TO OTHER CONTROL VARIABLES

Standard thermodynamics give rise to a number of (dc) linear-response coefficients. If the thermodynamic variables of interest are T , p , S , V , there are 24 coefficients of the form $(\partial a/\partial b)_c$ with a , b , and c chosen among T , p , S , V .⁴⁹ These coefficients form 12 pairs that are trivially related by inversion [e.g., $(\partial a/\partial b)_c = 1/(\partial b/\partial a)_c$]. As is well known, the 12 coefficients are not all independent, but related by various Maxwell relations (given below). There are the following eight basic linear-response coefficients (where the specific heats are per unit volume and the last three coefficients have no generally accepted names):

$$\begin{aligned}
 \text{isochoric specific heat: } c_V &\equiv \frac{T}{V} \left(\frac{\partial S}{\partial T} \right)_V; \\
 \text{isobaric specific heat: } c_p &\equiv \frac{T}{V} \left(\frac{\partial S}{\partial T} \right)_p; \\
 \text{isothermal compressibility: } \kappa_T &\equiv -\frac{1}{V} \left(\frac{\partial V}{\partial p} \right)_T; \\
 \text{adiabatic compressibility: } \kappa_S &\equiv -\frac{1}{V} \left(\frac{\partial V}{\partial p} \right)_S; \\
 \text{isobaric expansion coefficient:} \\
 \alpha_p &\equiv \frac{1}{V} \left(\frac{\partial V}{\partial T} \right)_p = -\frac{1}{V} \left(\frac{\partial S}{\partial p} \right)_T; \\
 \text{"adiabatic contraction coefficient:"} \\
 \alpha_S &\equiv -\frac{1}{V} \left(\frac{\partial V}{\partial T} \right)_S = \frac{1}{V} \left(\frac{\partial S}{\partial p} \right)_V; \\
 \text{"isochoric pressure coefficient:"} \\
 \beta_V &\equiv \left(\frac{\partial p}{\partial T} \right)_V = \left(\frac{\partial S}{\partial V} \right)_T; \\
 \text{"adiabatic pressure coefficient:"} \\
 \beta_S &\equiv \left(\frac{\partial p}{\partial T} \right)_S = \left(\frac{\partial S}{\partial V} \right)_p.
 \end{aligned}
 \tag{A1}$$

Consider harmonically varying scalar thermal and mechanical perturbations of equilibrium for a small volume element. "Small" here means that its linear dimensions are much smaller than both the heat diffusion length and the sound wavelength corresponding to the frequency under consideration, implying that the perturbations may be regarded as homogeneous over the small volume element. Let $\delta T(\omega)$, $\delta p(\omega)$, $\delta s(\omega)$, $\delta v(\omega)$ denote the complex amplitudes of perturbations varying with time as $\propto \exp(i\omega t)$ and define the intensive variables $v \equiv V/V_0$ and $s \equiv S/V_0$ where V_0 is the equilibrium volume. If small perturbations around temperature T_0 are considered, following Eq. (A1) one defines the following complex frequency-dependent linear-response quantities (where according to the so-called correspondence principle⁵⁰ all thermodynamic relations survive and the Maxwell relations become Onsager reciprocity relations⁴⁸):

$$\begin{aligned}
 \text{isochoric specific heat: } c_V(\omega) &\equiv T_0 \left(\frac{\delta s(\omega)}{\delta T(\omega)} \right)_V; \\
 \text{isobaric specific heat: } c_p(\omega) &\equiv T_0 \left(\frac{\delta s(\omega)}{\delta T(\omega)} \right)_p; \\
 \text{isothermal compressibility: } \kappa_T(\omega) &\equiv -\left(\frac{\delta v(\omega)}{\delta p(\omega)} \right)_T; \\
 \text{adiabatic compressibility: } \kappa_S(\omega) &\equiv -\left(\frac{\delta v(\omega)}{\delta p(\omega)} \right)_S; \\
 \text{isobaric expansion coefficient:} \\
 \alpha_p(\omega) &\equiv \left(\frac{\delta v(\omega)}{\delta T(\omega)} \right)_p = -\left(\frac{\delta s(\omega)}{\delta p(\omega)} \right)_T; \\
 \text{"adiabatic contraction coefficient:"} \\
 \alpha_S(\omega) &\equiv -\left(\frac{\delta v(\omega)}{\delta T(\omega)} \right)_S = \left(\frac{\delta s(\omega)}{\delta p(\omega)} \right)_V; \\
 \text{"isochoric pressure coefficient:"} \\
 \beta_V(\omega) &\equiv \left(\frac{\delta p(\omega)}{\delta T(\omega)} \right)_V = \left(\frac{\delta s(\omega)}{\delta v(\omega)} \right)_T; \\
 \text{"adiabatic pressure coefficient:"} \\
 \beta_S(\omega) &\equiv \left(\frac{\delta p(\omega)}{\delta T(\omega)} \right)_S = \left(\frac{\delta s(\omega)}{\delta v(\omega)} \right)_p.
 \end{aligned}
 \tag{A2}$$

The general procedure now works as follows. Let $(\delta X(\omega), \delta Y(\omega))$ denote the amplitudes of two periodically varying thermodynamic variables considered as control variables and $(\delta Z(\omega), \delta W(\omega))$ the remaining two periodically varying variables. The relationship between the two sets of variables generally takes the form

$$\begin{pmatrix} \delta Z(\omega) \\ \delta W(\omega) \end{pmatrix} = \begin{pmatrix} a_{11}(\omega) & a_{12}(\omega) \\ a_{21}(\omega) & a_{22}(\omega) \end{pmatrix} \begin{pmatrix} \delta X(\omega) \\ \delta Y(\omega) \end{pmatrix}. \quad (\text{A3})$$

In the case of a single order parameter ε —compare to Eq. (30)—we can write (where the 2×3 -matrix is real and frequency independent)

$$\begin{pmatrix} \delta Z(\omega) \\ \delta W(\omega) \end{pmatrix} = \begin{pmatrix} a_{11}^\infty & a_{12}^\infty & b_1 \\ a_{21}^\infty & a_{22}^\infty & b_2 \end{pmatrix} \begin{pmatrix} \delta X(\omega) \\ \delta Y(\omega) \\ \delta \varepsilon(\omega) \end{pmatrix}. \quad (\text{A4})$$

Comparing to Eq. (A3), when Y does not vary we get

$$\left. \begin{aligned} a_{11}(\omega) &= a_{11}^\infty + b_1 \left(\frac{\delta \varepsilon(\omega)}{\delta X(\omega)} \right)_Y \\ a_{21}(\omega) &= a_{21}^\infty + b_2 \left(\frac{\delta \varepsilon(\omega)}{\delta X(\omega)} \right)_Y \end{aligned} \right\} \Rightarrow \frac{a_{21}''(\omega)}{a_{11}''(\omega)} = \frac{b_2}{b_1} \equiv \gamma_{XY}, \quad (\text{A5})$$

and when X does not vary

$$\left. \begin{aligned} a_{12}(\omega) &= a_{12}^\infty + b_1 \left(\frac{\delta \varepsilon(\omega)}{\delta Y(\omega)} \right)_X \\ a_{22}(\omega) &= a_{22}^\infty + b_2 \left(\frac{\delta \varepsilon(\omega)}{\delta Y(\omega)} \right)_X \end{aligned} \right\} \Rightarrow \frac{a_{22}''(\omega)}{a_{12}''(\omega)} = \frac{b_2}{b_1} = \gamma_{XY}. \quad (\text{A6})$$

In principle there are six different choices of control variables. Below we treat the four natural cases where the input variables consist of one from the (S, T) “energy bond”^{51,52} and one from the $(-p, V)$ energy bond, and similarly for the output variables. In each case the signs are chosen to make the response matrix symmetric. Via Eqs. (A5) and (A6) in each of the four cases the three imaginary (loss) parts of the relevant linear-response functions are proportional. The four cases are detailed below, where the explicit amplitude frequency dependence is left out for simplicity of notation.

1. Control variables δT and $-\delta p$

This case was considered in the main paper, but is included here for completeness

$$\begin{pmatrix} \delta s \\ \delta v \end{pmatrix} = \begin{pmatrix} c_p(\omega)/T_0 & \alpha_p(\omega) \\ \alpha_p(\omega) & \kappa_T(\omega) \end{pmatrix} \begin{pmatrix} \delta T \\ -\delta p \end{pmatrix}. \quad (\text{A7})$$

Applying Eqs. (A5) and (A6) to this we get

$$\frac{T_0 \alpha_p''(\omega)}{c_p''(\omega)} = \gamma_{Tp} = \frac{\kappa_T''(\omega)}{\alpha_p''(\omega)}, \quad (\text{A8})$$

and thus

$$\Lambda_{Tp}(\omega) \equiv \frac{c_p''(\omega) \kappa_T''(\omega)}{T_0 [\alpha_p''(\omega)]^2} = 1. \quad (\text{A9})$$

2. Control variables δs and δv

$$\begin{pmatrix} \delta T \\ -\delta p \end{pmatrix} = \begin{pmatrix} T_0/c_V(\omega) & -1/\alpha_S(\omega) \\ -1/\alpha_S(\omega) & 1/\kappa_S(\omega) \end{pmatrix} \begin{pmatrix} \delta s \\ \delta v \end{pmatrix}. \quad (\text{A10})$$

Applying Eqs. (A5) and (A6) to this we get

$$-\frac{(1/\alpha_S(\omega))''}{(T_0/c_V(\omega))''} = \gamma_{SV} = -\frac{(1/\kappa_S(\omega))''}{(1/\alpha_S(\omega))''} \quad (\text{A11})$$

and thus

$$\Lambda_{SV}(\omega) \equiv \frac{(T_0/c_V(\omega))''(1/\kappa_S(\omega))''}{[(1/\alpha_S(\omega))'']^2} = 1. \quad (\text{A12})$$

3. Control variables δs and $-\delta p$

$$\begin{pmatrix} \delta T \\ -\delta v \end{pmatrix} = \begin{pmatrix} T_0/c_p(\omega) & -1/\beta_S(\omega) \\ -1/\beta_S(\omega) & -\kappa_S(\omega) \end{pmatrix} \begin{pmatrix} \delta s \\ -\delta p \end{pmatrix}. \quad (\text{A13})$$

Applying Eqs. (A5) and (A6) to this we get

$$-\frac{(1/\beta_S(\omega))''}{(T_0/c_p(\omega))''} = \gamma_{Sp} = \frac{\kappa_S''(\omega)}{(1/\beta_S(\omega))''} \quad (\text{A14})$$

and thus

$$\Lambda_{Sp}(\omega) \equiv -\frac{(T_0/c_p(\omega))'' \kappa_S''(\omega)}{[(1/\beta_S(\omega))'']^2} = 1. \quad (\text{A15})$$

4. Control variables δT and δv

$$\begin{pmatrix} \delta s \\ -\delta p \end{pmatrix} = \begin{pmatrix} c_V(\omega)/T_0 & -\beta_V(\omega) \\ -\beta_V(\omega) & -1/\kappa_T(\omega) \end{pmatrix} \begin{pmatrix} \delta T \\ -\delta v \end{pmatrix}. \quad (\text{A16})$$

Applying Eqs. (A5) and (A6) to this we get

$$-\frac{T_0 \beta_V''(\omega)}{c_V''(\omega)} = \gamma_{TV} = \frac{(1/\kappa_T(\omega))''}{\beta_V''(\omega)} \quad (\text{A17})$$

and thus

$$\Lambda_{TV}(\omega) \equiv -\frac{c_V''(\omega)(1/\kappa_T(\omega))''}{T_0 [\beta_V''(\omega)]^2} = 1. \quad (\text{A18})$$

For each case we showed above that, if there is a single-order parameter, the dynamic Prigogine-Defay ratio is unity. Below we proceed to prove that, conversely, if one of the dynamic Prigogine-Defay ratios is unity at some frequency, then this dynamic Prigogine-Defay ratio is unity at all frequencies and there is a single-order parameter. In particular, if one dynamic Prigogine-Defay ratio is unity at one frequency, all dynamic Prigogine-Defay ratios are unity at all frequencies.

In the periodic situation the dissipation is proportional to $\text{Im}[\delta T(\omega) \delta s^*(\omega) - \delta p(\omega) \delta v^*(\omega)]$.^{48,53} The requirement of positive dissipation implies that all four dynamic Prigogine-Defay ratios are larger than or equal to unity; this follows by considering the special case of in-phase input variables in which case it is easy to show that the determinant of the imaginary response matrix must be non-negative to have positive dissipation. If one of the dynamic Prigogine-Defay ratios is unity at some frequency ω , the determinant of the imaginary part of the corresponding response matrix is zero. This implies that there is an eigenvector of the imaginary response matrix with zero eigenvalue. Thus the dynamic Prigogine-Defay ratio is unity if and only if a thermodynamic cycle exists with zero dissipation. It follows that, in one of cases 2–4 the dynamic Prigogine-Defay ratio is unity

at frequency ω , then $\Lambda_{Tp}(\omega)=1$. This implies that $\Lambda_{Tp}(\omega)=1$ at all frequencies (Sec. III), and that there is a single order parameter ε such that S and V are given by Eq. (29). These equations are easily rewritten to give the required output variables in terms of the input variables and ε . This implies that the relevant dynamic Prigogine-Defay ratio is unity at all frequencies, and that all other dynamic Prigogine-Defay ratios are also unity at all frequencies.

- ¹R. O. Davies and G. O. Jones, Proc. R. Soc. London, Ser. A **217**, 26 (1952).
- ²R. O. Davies and G. O. Jones, Adv. Phys. **2**, 370 (1953).
- ³I. Prigogine and R. Defay, *Chemical Thermodynamics* (Longman, London, 1954).
- ⁴M. Goldstein, J. Chem. Phys. **39**, 3369 (1963).
- ⁵M. Goldstein, in *Modern Aspects of the Vitreous State*, edited by J. D. Mackenzie (Butterworths Scientific, London, 1964), Vol. 3, p. 90.
- ⁶C. A. Angell and W. Sichina, Ann. N.Y. Acad. Sci. **279**, 53 (1976).
- ⁷S. Brawer, *Relaxation in Viscous Liquids and Glasses* (American Ceramic Society, Columbus, OH, 1985).
- ⁸S. V. Nemilov, *Thermodynamic and Kinetic Aspects of the Vitreous State* (CRC, Boca Raton, FL, 1995).
- ⁹E. Donth, *The Glass Transition* (Springer, Berlin, 2001).
- ¹⁰C. T. Moynihan, P. B. Macedo, C. J. Montrose, C. J. Montrose, P. K. Gupta, M. A. DeBolt, J. F. Dill, B. E. Dom, P. W. Drake, A. J. Easteal, P. B. Elterman, R. P. Moeller, H. Sasabe, and J. A. Wilder, Ann. N.Y. Acad. Sci. **279**, 15 (1976).
- ¹¹H.-J. Oels and G. Rehage, Macromolecules **10**, 1036 (1977).
- ¹²P. Zoller, J. Polym. Sci., Polym. Phys. Ed. **20**, 1453 (1982).
- ¹³H. Wendt and R. Richert, Phys. Rev. E **61**, 1722 (2000).
- ¹⁴R. Böhmer, G. Diezemann, G. Hinze, and E. Rössler, Prog. Nucl. Magn. Reson. Spectrosc. **39**, 191 (2001).
- ¹⁵R. Richert and S. Weinstein, Phys. Rev. Lett. **97**, 095703 (2006).
- ¹⁶R.-J. Roe, J. Appl. Phys. **48**, 4085 (1977).
- ¹⁷I. M. Hodge, J. Non-Cryst. Solids **169**, 211 (1994).
- ¹⁸C. T. Moynihan and P. K. Gupta, J. Non-Cryst. Solids **29**, 143 (1978).
- ¹⁹C. T. Moynihan and A. V. Lesikar, Ann. N.Y. Acad. Sci. **371**, 151 (1981).
- ²⁰E. A. DiMarzio, J. Appl. Phys. **45**, 4143 (1974).
- ²¹M. Goldstein, J. Appl. Phys. **46**, 4153 (1975).
- ²²A. V. Lesikar and C. T. Moynihan, J. Chem. Phys. **72**, 6422 (1980).
- ²³Th. M. Nieuwenhuizen, Phys. Rev. Lett. **79**, 1317 (1997).
- ²⁴M. R. H. Javaheri and R. V. Chamberlin, J. Chem. Phys. **125**, 154503 (2006).
- ²⁵J. H. R. Clarke, J. Chem. Soc., Faraday Trans. 2 **75**, 1371 (1979).
- ²⁶E. La Nave, S. Mossa, and F. Sciortino, Phys. Rev. Lett. **88**, 225701 (2002).
- ²⁷M. S. Shell, P. G. Debenedetti, E. L. Nave, and F. Sciortino, J. Chem. Phys. **118**, 8821 (2003).
- ²⁸S. Mossa and F. Sciortino, Phys. Rev. Lett. **92**, 045504 (2004).

- ²⁹F. Sciortino, J. Stat. Mech.: Theory Exp. 2005, P05015.
- ³⁰J. C. Dyre and N. B. Olsen, Phys. Rev. Lett. **91**, 155703 (2003).
- ³¹R. Böhmer, G. Diezemann, B. Geil, G. Hinze, A. Nowaczyk, and M. Winterlich, Phys. Rev. Lett. **97**, 135701 (2006).
- ³²C. M. Roland, S. Hensel-Bielowka, M. Paluch, and R. Casalini, Rep. Prog. Phys. **68**, 1405 (2005).
- ³³R. J. Speedy, J. Phys. Chem. B **103**, 4060 (1999).
- ³⁴J. Wu, J. Appl. Polym. Sci. **71**, 143 (1999).
- ³⁵N. B. Olsen, T. Christensen, and J. C. Dyre, Phys. Rev. Lett. **86**, 1271 (2001).
- ³⁶B. Jakobsen, K. Niss, and N. B. Olsen, J. Chem. Phys. **123**, 234511 (2005).
- ³⁷T. Christensen *et al.*, to be published.
- ³⁸M. Goldstein, J. Chem. Phys. **51**, 3728 (1969).
- ³⁹R. G. Palmer, Adv. Phys. **31**, 669 (1982).
- ⁴⁰F. H. Stillinger and T. A. Weber, Phys. Rev. A **28**, 2408 (1983).
- ⁴¹T. B. Schröder, S. Sastry, J. C. Dyre, and S. C. Glotzer, J. Chem. Phys. **112**, 9834 (2000).
- ⁴²The relation $\partial G/\partial P_n = \text{const}$ leads to $G_n + k_B T \ln P_n^{\text{eq}} + k_B T = \text{const}$. Insert this into Eq. (4) to find $G_n + k_B T \ln P_n^{\text{eq}} = G$, then isolate P_n^{eq} to get the desired result.
- ⁴³N. G. Van Kampen, *Stochastic Processes in Physics and Chemistry* (North Holland, Amsterdam, 1981).
- ⁴⁴We have $\partial \ln P_m^{\text{eq}}/\partial T = [-1/k_B T](\partial(G_m - G)/\partial T - (G_m - G)/T) = (1/k_B T) \times (\partial S/\partial P_m - S + k_B)$ and $\partial \ln P_m^{\text{eq}}/\partial(-p) = [-1/k_B T_0][\partial(G_m - G)/\partial(-p)] = (1/k_B T_0)(\partial V/\partial P_m - V)$.
- ⁴⁵L. E. Reichl, *A Modern Course in Statistical Physics*, 2nd ed. (Wiley, New York, 1998).
- ⁴⁶If the eigenvalues of Y are denoted by λ_k with corresponding eigenvectors e_k , there are $N-1$ negative eigenvalues and one zero eigenvalue.⁴³ Equation (23) implies that for any vector x we have $\langle x|A(\omega)|x \rangle = (1/k_B T_0) \sum_{\lambda_k < 0} \langle Rx|e_k \rangle \langle e_k|Rx \rangle \lambda_k / (\lambda_k - i\omega)$ (where the sum is restricted to the $N-1$ negative eigenstates). Letting $\omega \rightarrow 0$ we find that $\langle x|A(0)|x \rangle \geq 0$, showing that $A(0)$ is positive semidefinite. For the imaginary part, we find that $\langle x|A''(\omega)|x \rangle = (1/k_B T_0) \sum_{\lambda_k < 0} \langle Rx|e_k \rangle \langle e_k|Rx \rangle \lambda_k \omega / (\lambda_k^2 + \omega^2) \leq 0$ whenever $\omega > 0$; thus $A''(\omega)$ is negative semidefinite. In both cases, equality applies if and only if the vector Rx lies in the one-dimensional eigenspace of Y corresponding to the zero eigenvalue. Thus equality applies if and only if $(Rx)_n \propto (P_n^0)^{1/2}$, or $x \propto (1, \dots, 1)$.
- ⁴⁷P. K. Gupta and C. T. Moynihan, J. Chem. Phys. **65**, 4136 (1976).
- ⁴⁸J. Meixner and H. G. Reik, in *Principien der Thermodynamik und Statistik*, edited by S. Flügge, Handbuch der Physik, Vol. 3 (Springer, Berlin, 1959), p. 413.
- ⁴⁹J. I. Berg and A. R. Cooper, J. Chem. Phys. **68**, 4481 (1978).
- ⁵⁰R. M. Christensen, *Theory of Viscoelasticity*, 2nd ed. (Academic, New York, 1982).
- ⁵¹G. F. Oster, A. S. Perelson, and A. Katchalsky, Q. Rev. Biophys. **6**, 1 (1973).
- ⁵²D. C. Mikulecky, *Applications of Network Thermodynamics to Problems in Biomedical Engineering* (New York University, New York, 1993).
- ⁵³J. Bataille and J. Kestin, J. Non-Equil. Thermodyn. **4**, 229 (1979).