

Dominance of shear elastic energy far from a point defect in a solid

Dyre, Jeppe

Published in:
Physical Review B. Condensed Matter and Materials Physics

DOI:
[10.1103/PhysRevB.75.092102](https://doi.org/10.1103/PhysRevB.75.092102)

Publication date:
2007

Document Version
Publisher's PDF, also known as Version of record

Citation for published version (APA):
Dyre, J. (2007). Dominance of shear elastic energy far from a point defect in a solid. *Physical Review B. Condensed Matter and Materials Physics*, 75(9), 092102-1 - 092102-4.
<https://doi.org/10.1103/PhysRevB.75.092102>

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain.
- You may freely distribute the URL identifying the publication in the public portal.

Take down policy

If you believe that this document breaches copyright please contact rucforsk@kb.dk providing details, and we will remove access to the work immediately and investigate your claim.

Dominance of shear elastic energy far from a point defect in a solid

Jeppe C. Dyre

*DNRF Centre of Viscous Liquid Dynamics “Glass and Time,” IMFUFA, Department of Sciences, Roskilde University,
Postbox 260, DK-4000 Roskilde, Denmark*

(Received 16 May 2006; revised manuscript received 22 January 2007; published 12 March 2007)

It is shown that the elastic energy far from a point defect in an isotropic solid is mainly shear elastic energy. The calculation, which is based on a standard dipole expansion, shows that less than 10% of the distant point defect energy is associated with volume changes, no matter how large or small the bulk modulus is compared to the shear modulus.

DOI: [10.1103/PhysRevB.75.092102](https://doi.org/10.1103/PhysRevB.75.092102)

PACS number(s): 61.72.Ji

An isotropic solid just has two independent elastic constants, the shear modulus G and the bulk modulus K . It has been suggested that when a physical property depends on both G and K , the dependence on the shear modulus is often the most important.¹ Examples of this “shear dominance” were given by Granato² in his profound paper from 1992; they include the fact that defect energies vary only slightly with the bulk modulus, but are linearly dependent on the shear modulus (for Cu, he estimated that only about 3% of the energy of an interstitial is bulk elastic energy). In Ref. 1 which dealt with the non-Arrhenius viscosity of viscous liquids and its possible explanation in terms of temperature-dependent instantaneous elastic constants,³ the following result was proved: If temperature dependence is quantified in terms of log-log derivatives, at least 92% of the temperature dependence of the molecular vibrational mean-square displacement over temperature comes from the instantaneous shear modulus; at most 8% is due to that of the instantaneous bulk modulus.

The question is how general shear dominance is: Is it coincidental or is it a fairly general theme of three-dimensional elasticity? Of course, a property such as the Poisson ratio depends equally on the bulk and shear moduli, so it cannot be a completely general phenomenon. Nevertheless, there are so many examples that shear dominance deserves to be investigated. As one contribution to shed light on this question, we calculate below the maximum ratio of bulk elastic energy to shear elastic energy far from an arbitrary point defect in an isotropic solid. Based on a standard dipole expansion,⁴ it is shown that less than 10% of the distant elastic energy is bulk elastic energy, i.e., associated with density changes.

Although our main objective is to identify the dominant contribution to the elastic energy far from a point defect, it should be noted that according to Zener’s “strain energy model”⁵ most energy associated with a point defect is elastic. Elastic energies of point defects fall off rapidly (as r^{-6}) as evident from Eshelby’s famous solution of the problem of an ellipsoidal inclusion,^{6–12} a result which is general. This means, of course, that most of the elastic energy is located close to the point defect and that a dipole expansion is not realistic for calculating the total defect energy. Nevertheless, our results may be taken as an indication of what contributes most to the total defect energy, the shear or the bulk elastic energies in the defect surroundings. Moreover, the nature of the far-field deformation is important for understanding and

modeling the long-range properties of defect-defect interactions. If, for instance, the displacement field is dominated by shear displacements, a defect will only interact weakly with another defect far away if the latter is dilatational close to its center.

Some time ago, Andreev discussed the unique topological characteristics of point defects in three dimensions.¹³ A comprehensive review of point defect properties emphasizing the vacancy was given by Kraftmakher.¹⁴ The question of the nature of the deformation far from a point defect is relevant also for applications in materials science, e.g., for understanding fracture.⁹ In its macroscopic description, the question of the far-field properties of a point defect was studied because of its importance for understanding the mechanical properties of polycrystals and composites.^{4,6,15} In this context, Onaka recently calculated the elastic shear energy due to a macroscopic point defect (an “inclusion”),¹⁶ but did not study the general case to find the ratio between shear and bulk energy (see also Ref. 12). Garikipati *et al.*¹⁷ recently discussed the role of continuum elasticity in determining the formation energy of a point defect utilizing Eshelby’s result for the work done by an external stress during the transformation of an inclusion;⁶ this interesting paper also elucidated the limitations of this approach as compared to atomistic calculations. We mention these works also to emphasize the continuing interest in the far-field properties of point defects and their macroscopic analogies.

First some preliminaries: We use the standard Einstein summation convention. The point defect is located at the origin and is modeled as follows: Imagine a small sphere of radius R surrounding the point defect with all atoms within the sphere removed. The effect of the defect on the surroundings is represented by a suitable distribution of external forces F_i applied to the surface of the sphere. We define the tensor λ_{ij} as the following integral over the surface of the sphere (where dA is the area element):

$$\lambda_{ij} = \oint_{|y|=R} F_i(\mathbf{y}) y_j dA. \quad (1)$$

Because the force distribution models the effect of the atoms within the sphere on the surroundings, the angular momentum of the force distribution must be zero. This implies that λ is symmetric: $\lambda_{ij} = \lambda_{ji}$.

Sharp brackets $\langle \rangle_r$, referred to as “averages,” denote integrations over the surface of a sphere with radius $r \gg R$ centered at the origin. The following identities become useful later:

$$\langle x_i x_j \rangle_r = \frac{r^2}{3} \delta_{ij} \quad (2)$$

and

$$\langle x_i x_j x_k x_l \rangle_r = \frac{r^4}{15} (\delta_{ij} \delta_{kl} + \delta_{ik} \delta_{jl} + \delta_{il} \delta_{jk}). \quad (3)$$

If (λ_{xx}) is an abbreviation of $\lambda_{ij} x_i x_j$, we find from these identities that

$$\langle (\lambda_{xx}) \rangle_r = \frac{r^2}{3} \text{tr} \lambda \quad (4)$$

and

$$\langle (\lambda_{xx})^2 \rangle_r = \frac{r^4}{15} [(\text{tr} \lambda)^2 + 2 \text{tr}(\lambda^2)]. \quad (5)$$

Moreover, if λx is the vector whose i th component is $\lambda_{ij} x_j$, we have

$$\langle (\lambda^2_{xx}) \rangle_r = \langle (\lambda x)^2 \rangle_r = \frac{r^2}{3} \text{tr}(\lambda^2). \quad (6)$$

As mentioned, far from the defect both the bulk and the shear elastic energies vary with the distance from the origin as r^{-6} . When one averages over a sphere with radius $r \gg R$, the result for both the bulk and the shear elastic energy must be a scalar varying with distance as r^{-6} that is of second order in the forces F_i . It follows from the calculation below that these two scalars are both uniquely determined by G , K , and the λ matrix. Consequently, because these two scalar functions are of second order in the forces, the ratio of bulk to shear elastic energy must have the following general structure:

$$\frac{\text{Bulk elastic energy}}{\text{Shear elastic energy}} = \frac{A(\text{tr} \lambda)^2 + B \text{tr}(\lambda^2)}{C(\text{tr} \lambda)^2 + D \text{tr}(\lambda^2)}. \quad (7)$$

Defining $\alpha = \text{tr}(\lambda^2) / (\text{tr} \lambda)^2$, this ratio is $(A+B\alpha)/(C+D\alpha)$. The quantity α varies between $1/3$ and ∞ : By normalizing we may assume that $\text{tr} \lambda = 1$; if the eigenvalues are denoted by μ_i , we thus have $\mu_1 + \mu_2 + \mu_3 = 1$ and $\alpha = \mu_1^2 + \mu_2^2 + \mu_3^2$. From this it follows that α varies between $1/3$ and ∞ . Since the energy ratio of Eq. (7) is a monotonous function of α and since perfect isotropy ($\alpha = 1/3$) implies zero bulk elastic energy (in this case, the displacement field is radially symmetric varying as r^{-2} , which implies no volume changes), the maximum bulk to shear elastic energy ratio arises in the limit $\alpha \rightarrow \infty$. Thus in the calculation below, we may ignore all terms with $\text{tr} \lambda$ and keep only terms with a $\text{tr}(\lambda^2)$ factor.

Poisson's ratio σ is defined¹⁸ by

$$\sigma = \frac{1}{2} \frac{3K - 2G}{3K + G}. \quad (8)$$

If a force \mathbf{F} is applied at the origin of an isotropic elastic continuum, the displacement field at the point (x', y', z') is given¹⁸ by

$$\mathbf{u}(x', y', z') \propto \frac{(3 - 4\sigma)\mathbf{F} + (\mathbf{F} \cdot \mathbf{n}')\mathbf{n}'}{r'}, \quad (9)$$

where $r'^2 = x'^2 + y'^2 + z'^2$ and $\mathbf{n}' = (x', y', z')/r'$ is the unit vector pointing from the origin to (x', y', z') . It is convenient to introduce the variable

$$\Lambda \equiv 2 - 4\sigma, \quad (10)$$

in terms of which Eq. (9) becomes

$$u_i \propto (\Lambda + 1) \frac{F_i}{r'} + \frac{F_j n'_j n'_i}{r'}. \quad (11)$$

We proceed to perform a standard dipole expansion by first noting that if \mathbf{y} is the coordinate for a point on the small sphere surrounding the defect ($|\mathbf{y}| = R$) and \mathbf{x} is the coordinate for the point of interest far away, to lowest order in $|\mathbf{y}|/|\mathbf{x}| = R/|\mathbf{x}|$ we have, if $r \equiv |\mathbf{x}|$,

$$\begin{aligned} \frac{1}{|\mathbf{x} - \mathbf{y}|} &= (\mathbf{x}^2 + \mathbf{y}^2 - 2\mathbf{x} \cdot \mathbf{y})^{-1/2} \\ &= r^{-1} \left(1 - 2 \frac{\mathbf{x} \cdot \mathbf{y}}{r^2} \right)^{-1/2} \\ &= r^{-1} + \frac{\mathbf{x} \cdot \mathbf{y}}{r^3}. \end{aligned} \quad (12)$$

Similarly,

$$\begin{aligned} \frac{1}{|\mathbf{x} - \mathbf{y}|^3} &= (\mathbf{x}^2 + \mathbf{y}^2 - 2\mathbf{x} \cdot \mathbf{y})^{-3/2} \\ &= r^{-3} \left(1 - 2 \frac{\mathbf{x} \cdot \mathbf{y}}{r^2} \right)^{-3/2} \\ &= r^{-3} + 3 \frac{\mathbf{x} \cdot \mathbf{y}}{r^5}. \end{aligned} \quad (13)$$

To calculate the displacement field at point \mathbf{x} , we first note that when the force $F_i(\mathbf{y})$ is integrated over the small sphere radius R , the result is zero. Thus when one integrates over the small sphere, the first term of Eq. (11) to lowest order in $1/r$ becomes

$$\begin{aligned} (\Lambda + 1) \oint_{|\mathbf{y}|=R} \frac{F_i(\mathbf{y})}{|\mathbf{x} - \mathbf{y}|} dA &= (\Lambda + 1) \oint_{|\mathbf{y}|=R} F_i(\mathbf{y}) \frac{\mathbf{x} \cdot \mathbf{y}}{r^3} dA \\ &= (\Lambda + 1) r^{-3} \lambda_{ij} x_j. \end{aligned} \quad (14)$$

Similarly, to lowest order the second term of Eq. (11) gives the following contribution to the displacement field:

$$\begin{aligned}
& \oint_{|\mathbf{y}|=R} \frac{F_j(\mathbf{y})(x_j - y_j)(x_i - y_i)}{|\mathbf{x} - \mathbf{y}|^3} dA \\
&= \oint_{|\mathbf{y}|=R} F_j(\mathbf{y}) \left(r^{-3} + 3 \frac{\mathbf{x} \cdot \mathbf{y}}{r^5} \right) (x_j - y_j)(x_i - y_i) dA \\
&= -r^{-3} \lambda_{ij} x_j - r^{-3} \lambda_{jj} x_i + 3r^{-5} \lambda_{jl} x_j x_l x_i. \quad (15)
\end{aligned}$$

Thus, if proportionality is replaced by equality for simplicity of notation—which is ok because we only wish to calculate an energy ratio and have already dropped the overall proportionality constant of Eq. (9)—we find

$$u_i = \Lambda r^{-3} \lambda_{ij} x_j - r^{-3} \text{tr} \lambda x_i + 3r^{-5} \lambda_{jl} x_j x_l x_i. \quad (16)$$

Next we calculate the strain tensor. First, note that if ∂_k is the partial derivative with respect to x_k , we have $\partial_k r^{-n} = (-n)r^{-(n+2)} x_k$. Thus,

$$\begin{aligned}
\partial_k u_i &= -3\Lambda r^{-5} \lambda_{ij} x_j x_k + \Lambda r^{-3} \lambda_{ij} \delta_{jk} + 3r^{-5} \text{tr} \lambda x_i x_k \\
&\quad - r^{-3} \text{tr} \lambda \delta_{ik} - 15r^{-7} \lambda_{jl} x_j x_l x_i x_k + 3r^{-5} \lambda_{jl} \delta_{jk} x_l x_i \\
&\quad + 3r^{-5} \lambda_{jl} x_j \delta_{lk} x_i + 3r^{-5} \lambda_{jl} x_j x_l \delta_{ik}. \quad (17)
\end{aligned}$$

All terms in this expression vary with r as r^{-3} . Consequently, this term is common to the bulk and shear elastic energies and may be dropped from our calculation of their ratio. The calculation is simplified notationally by putting $r=1$ (or, equivalently, replacing x_i by x_i/r). When this convention is adopted, the strain tensor is given by [ignoring the factor 2 in the strain tensor definition, $u_{ik} = (\partial_i u_k + \partial_k u_i)/2$],

$$\begin{aligned}
u_{ik} &= 2[-\text{tr} \lambda + 3(\lambda_{xx})] \delta_{ik} + 2\Lambda \lambda_{ik} + 6 \text{tr} \lambda x_i x_k - 30(\lambda_{xx}) x_i x_k \\
&\quad - 3\Lambda (\lambda_{ij} x_j x_k + \lambda_{kj} x_j x_i) + 6\lambda_{kj} x_j x_i + 6\lambda_{ij} x_j x_k \\
&= 2[-\text{tr} \lambda + 3(\lambda_{xx})] \delta_{ik} + 2\Lambda \lambda_{ik} + [6 \text{tr} \lambda - 30(\lambda_{xx})] x_i x_k \\
&\quad + (6 - 3\Lambda) (\lambda_{ij} x_j x_k + \lambda_{kj} x_j x_i). \quad (18)
\end{aligned}$$

Throwing out terms with $\text{tr} \lambda$, we end with the following expression for the strain tensor:

$$\begin{aligned}
u_{ik} &= 6(\lambda_{xx}) \delta_{ik} + 2\Lambda \lambda_{ik} - 30(\lambda_{xx}) x_i x_k \\
&\quad + (6 - 3\Lambda) (\lambda_{ij} x_j x_k + \lambda_{kj} x_j x_i). \quad (19)
\end{aligned}$$

To calculate the bulk elastic energy, we need the trace of this which, when again terms with $\text{tr} \lambda$ are dropped, is given as ($x_i x_i = r^2$ is set equal to unity),

$$\text{tr} u = 18(\lambda_{xx}) - 30(\lambda_{xx}) + (6 - 3\Lambda) 2(\lambda_{xx}) = -6\Lambda(\lambda_{xx}). \quad (20)$$

The bulk elastic energy density¹⁸ averaged over the sphere with radius r (subsequently set equal to unity) is, when use is made of Eq. (5) and terms with $\text{tr} \lambda$ are ignored, given by

$$\begin{aligned}
\text{Bulk elastic energy} &= \frac{K}{2} \langle (\text{tr}(u))^2 \rangle_r \\
&= \frac{K}{2} 36\Lambda^2 \langle (\lambda_{xx})^2 \rangle_r \\
&= \frac{12}{5} K\Lambda^2 \text{tr}(\lambda^2). \quad (21)
\end{aligned}$$

To find the shear elastic energy, we need the transverse part of the strain tensor, u_{ik}^\perp (in terms of which the shear energy density is $G u_{ik}^\perp u_{ik}^\perp$) defined as:¹⁸

$$\begin{aligned}
u_{ik}^\perp &\equiv u_{ik} - \frac{1}{3} \text{tr}(u) \delta_{ik} = 2(3 + \Lambda)(\lambda_{xx}) \delta_{ik} + 2\Lambda \lambda_{ik} \\
&\quad - 30(\lambda_{xx}) x_i x_k + 3(2 - \Lambda) (\lambda_{ij} x_j x_k + \lambda_{kj} x_j x_i). \quad (22)
\end{aligned}$$

Squaring and summing all elements of the transverse strain tensor, which is required to calculate the shear elastic energy, lead to the following ($x_i x_i = r^2$ is again set equal to unity):

$$\begin{aligned}
u_{ik}^\perp u_{ik}^\perp &= 4(3 + \Lambda)^2 (\lambda_{xx})^2 3 + 4\Lambda^2 \text{tr}(\lambda^2) + 900(\lambda_{xx})^2 \\
&\quad + 9(2 - \Lambda)^2 [2(\lambda_{xx})^2 + 2(\lambda_{xx})^2] + 8\Lambda(3 + \Lambda)(\lambda_{xx}) \text{tr} \lambda \\
&\quad - 120(3 + \Lambda)(\lambda_{xx})^2 + 12(3 + \Lambda)(2 - \Lambda) 2(\lambda_{xx})^2 \\
&\quad - 120\Lambda(\lambda_{xx})^2 + 12\Lambda(2 - \Lambda) 2(\lambda^2_{xx}) - 180(2 - \Lambda) \\
&\quad \times (\lambda_{xx}) 2(\lambda_{xx}). \quad (23)
\end{aligned}$$

Averaging this expression (ignoring all $\text{tr} \lambda$ terms) leads to

$$\begin{aligned}
\langle u_{ik}^\perp u_{ik}^\perp \rangle_r &= \left[12(3 + \Lambda)^2 \frac{2}{15} + 4\Lambda^2 + 900 \frac{2}{15} \right. \\
&\quad + 18(2 - \Lambda)^2 \left(\frac{1}{3} + \frac{2}{15} \right) - 120(3 + \Lambda) \frac{2}{15} \\
&\quad + 24(3 + \Lambda)(2 - \Lambda) \frac{2}{15} - 120\Lambda \frac{2}{15} + 24\Lambda(2 - \Lambda) \frac{1}{3} \\
&\quad \left. - 360(2 - \Lambda) \frac{2}{15} \right] \text{tr}(\lambda^2) \\
&= \frac{2}{5} (7\Lambda^2 + 12\Lambda + 108) \text{tr}(\lambda^2). \quad (24)
\end{aligned}$$

Summarizing, we find that

$$\begin{aligned}
\frac{\text{Bulk elastic energy}}{\text{Shear elastic energy}} &\leq \frac{(12/5)K\Lambda^2}{(2/5)G(7\Lambda^2 + 12\Lambda + 108)} \\
&= \frac{K}{G} \frac{6\Lambda^2}{7\Lambda^2 + 12\Lambda + 108}. \quad (25)
\end{aligned}$$

In terms of the dimensionless variable

$$k \equiv \frac{K}{G}, \quad (26)$$

we have $\Lambda = 6/(3k + 1)$ which, when substituted into Eq. (25), leads to

$$\frac{\text{Bulk elastic energy}}{\text{Shear elastic energy}} \leq \frac{2k}{9k^2 + 8k + 4}. \quad (27)$$

The derivative of the fraction on the right with respect to k is zero when $2(9k^2 + 8k + 4) = 2k(18k + 8)$, implying $k = 2/3$. Thus the maximum bulk elastic energy is when $k = 2/3$. In conclusion,

$$\frac{\text{Bulk elastic energy}}{\text{Shear elastic energy}} \leq \frac{\text{Bulk elastic energy}}{\text{Shear elastic energy}} \left(k = \frac{2}{3} \right) \leq \frac{1}{10}. \quad (28)$$

More typically, $k=5/2$ leads to a maximum bulk shear ratio of 20/337, which is roughly 6%.

An important unsolved problem of condensed-matter physics is the origin of the non-Arrhenius average relaxation time of glass-forming liquids, where one generally observes an activation energy that increases quite a lot upon cooling. One class of theories are the elastic models recently reviewed in Ref. 3, according to which the activation energy is some linear combination of the instantaneous bulk and shear moduli. As regards the temperature dependence of the activation energy, the shear modulus completely dominates by contributing at least 90%¹. A so-called flow event—a jump in configuration space from one to another potential-energy minimum—is usually localized in real space. Since the surrounding ultraviscous liquid on the short time scale may be regarded as a solid, the molecular displacements may be regarded as those of a point defect (in a disordered solid, albeit). The main result of this Brief Report sheds light on the nature of flow events, because it once again emphasizes shear dominance—that the shear properties are much more important than the bulk.

In an interesting book from 1986, Varotsos and Alexopoulos (VA) discussed point defect energies in solids, as well as activation energies for point defect diffusion¹⁹. They concluded that these energies can always be written as the (isothermal) bulk modulus times a microscopic volume. Thus, according to VA, point defect energies and activation energies always scale with the bulk modulus. This result is at variance with the above calculation. In practical terms, of course, Poisson's ratio usually does not vary that much, so the bulk and shear moduli are roughly proportional. This means that, in practice, it is not easy to determine whether it is the bulk or the shear modulus that controls things. VA explicitly argued in their book that it is the bulk, *not* the shear modulus that is important, but they did not base this on precise calculations similar to the above. We hope the above calculation may encourage other researchers to look into the question; perhaps the short-range contribution that was not taken into account here could be bulk dominated. The idea that many important physical properties are controlled by simple quantities like the elastic moduli deserves to be fully investigated.

This work was supported by the Danish National Research Foundation's Centre for Viscous Liquid Dynamics "Glass and Time."

¹J. C. Dyre and N. B. Olsen, Phys. Rev. E **69**, 042501 (2004).

²A. V. Granato, Phys. Rev. Lett. **68**, 974 (1992).

³J. C. Dyre, Rev. Mod. Phys. **78**, 953 (2006).

⁴T. Mura, *Micromechanics of Defects in Solids*, 2nd ed. (Kluwer, Dordrecht, 1982).

⁵C. Zener, Trans. Am. Inst. Min., Metall. Pet. Eng. **147**, 361 (1942).

⁶J. D. Eshelby, Proc. R. Soc. London, Ser. A **241**, 376 (1957).

⁷R. Kienzler and G. Herrmann, Acta Mech. **125**, 73 (1997).

⁸S. Onaka, Philos. Mag. Lett. **80**, 367 (2000).

⁹R. Kienzler and G. Herrmann, Mech. Res. Commun. **29**, 521 (2002).

¹⁰S. F. Li, Int. J. Eng. Sci. **42**, 1215 (2004).

¹¹S. Matthies and G. W. Vinel, Solid State Phenom. **105**, 113

(2005).

¹²F. D. Fischer, H. J. Böhm, E. R. Oberaigner, and T. Waitz, Acta Mater. **54**, 151 (2006).

¹³A. F. Andreev, JETP Lett. **62**, 136 (1996).

¹⁴Y. Kraftmakher, Phys. Rep. **299**, 80 (1998).

¹⁵J. D. Eshelby, Prog. Solid Mech. **2**, 89 (1961).

¹⁶S. Onaka, Philos. Mag. Lett. **85**, 115 (2005).

¹⁷K. Garikipati, M. L. Falk, M. Bouville, B. Puchala, and H. Narayanan, J. Mech. Phys. Solids **54**, 1929 (2006).

¹⁸L. D. Landau and E. M. Lifshitz, *Theory of Elasticity*, 2nd ed. (Pergamon, London, 1970).

¹⁹P. A. Varotsos and K. D. Alexopoulos, *Thermodynamics of Point Defects and Their Relation with Bulk Properties* (North-Holland, Amsterdam, 1986).